

Comment on “Quantum Melting of the Quasi-Two-Dimensional Vortex Lattice in $\kappa-(\text{ET})_2\text{Cu}(\text{NCS})_2$ ”

Y. Kopelevich⁺ and P. Esquinazi^{*}

⁺*Instituto de Física, Unicamp, 13083-970 Campinas, São Paulo, Brasil*

^{*}*Abteilung Supraleitung und Magnetismus, Universität Leipzig, Linnéstr. 5, D-04103 Leipzig, Germany*

In a recent Letter Mola et al. [1] reported magnetization measurements $M(H, \theta)$ performed on the organic superconductor $\kappa-(\text{ET})_2\text{Cu}(\text{NCS})_2$ ($T_c = 9.1$ K) as a function of the magnetic field H applied at different angles θ with respect to the a -axis direction. The results [1] demonstrate: (a) the occurrence of pronounced irreversible magnetization $M_{\text{irr}}(H)$ jumps and (b) their sudden cessation for $H \geq H_m(T, \theta)$. The boundary line $H_m(T)$ has been interpreted by Mola et al. as the Q2D vortex lattice (VL) quantum melting phase transition line [1]. The purpose of this comment is to show that the results can be understood in a simple way without invoking “quantum melting phase transition”.

As has been recently reported in detail [2], the termination of flux jumps with field accompanied by a kink-or second magnetization peak (SMP)-like- anomaly in $M_{\text{irr}}(H)$ is also observed in conventional Nb superconducting films and can be naturally understood within the framework of the thermomagnetic flux-jump instability theory (TMI) [3] without invoking VL transformations. Using both global and local magnetization $M(H)$ measurements, it has been demonstrated that at low enough temperatures and at $H < H_{\text{SMP}}(T)$ TMI leads to the reduction of $|M_{\text{irr}}(H)|$ relative to the isothermal critical state value, and this is reestablished at $H \geq H_{\text{SMP}}(T)$ due to the decrease of the critical current density j_c with field [2]. It has been shown also [2] that the $H_{\text{SMP}}(T)$ can be approximated by the equation $H_{\text{SMP}}(T) = H_0(1 - (T/T_0)^2)$, where H_0 is a free parameter and $T_0 < T_c$ depends on the intrinsic pinning properties as well as on the effective film size $s_{\text{eff}} \sim (wd/2)^{1/2}$ (w and d being the film width and thickness) of the sample.

Figure 1 shows the “melting” line $H_m(T/T_0)$ obtained in [1] for a crystal with dimensions $l \times w \times d = 1 \times 1 \times 0.3$ mm³. To facilitate the comparison with the Nb films we have normalized the temperature scale by the value $T_0 = 0.152$ K. As can be seen in Fig. 1, the $H_m(T/T_0)$ line is similar to the $H_{\text{SMP}}(T)$ lines obtained in Nb films. As for the Nb films, $H_m(T)$ can be very well fitted by the equation $H_m(T) = H_0(1 - (T/T_0)^2)$ with $\mu_0 H_0 = 3.8$ T and $T_0 = 0.152$ K, whereas T_0 for the Nb films runs from ~ 4 K to ~ 7 K depending on the effective size of the films [2]. The difference in T_0 between the two superconductors is mainly due to the difference in the magnitude of pinning. The TMI theory [3] predicts a critical effective sample size $s_{\text{crit}} = 10H_{fj}/4\pi j_c$ below which no flux jumps appear. Here H_{fj} is the field at which first flux jump occurs. Taking $H_{fj} \sim 1 - 2$ kOe

and in-plane $j_c(0) \sim 4 \times 10^4$ A/cm² [1,4] one gets $s_{\text{crit}} \sim 0.2 - 0.4$ mm which coincides with the effective crystal size $s_{\text{eff}} \sim 0.4$ mm, implying that the instability criterion ($s_{\text{crit}} < s_{\text{eff}}$) can be reached at very low temperatures ($T_0/T_c \ll 1$) as the experiment in [1] demonstrates.




FIG. 1. (●) : $H_m(T)$ data points from [1]. The solid lines correspond to the equation $H(T) = H_0(1 - (T/T_0)^2)$. $\mu_0 H_0 = 3.8$ T and $T_0 = 0.152$ K ($\mu_0 H_0 = 0.7$ T and $T_0 = 4 \dots 7$ K) for the upper (lower) data points. The lower data points correspond to $H_{\text{SMP}}(T)$ obtained for Nb films [2].

The increase of H_m with θ reported in [1] can be understood as follows. First of all, note that within the TMI approach the expected decrease of H_m with θ due to reduction of s_{eff} from ~ 0.4 mm to $s_{\text{eff}} \sim d = 0.3$ mm [5] should be negligible. However, the activation energy of pancake vortices increases with θ [6]. Therefore, a larger applied field is needed to stabilize the isothermal critical state [7]. We note further that the coincidence of a single $H_m(\theta)$ -data point obtained for the second (larger) crystal with the reported $H_m(\theta)$ [1] can be merely due to a difference in j_c . In summary the $H_m(T, \theta)$ obtained in [1] is simply the boundary in the $H - T$ plane that separates the TMI regime from the isothermal Bean-like critical state.

-
- [1] M. M. Mola et al., Phys. Rev. Lett. **86**, 2130 (2001).
 - [2] P. Esquinazi et al., Phys. Rev. B **60**, 12454 (1999) and references therein.
 - [3] R. G. Mints and A. L. Rakhmanov, Rev. Mod. Phys. **53**,

551 (1981) and references therein.

[4] M. M. Mola et al., cond-mat/0011227.

[5] P. S. Swartz and C. P. Bean, J. Appl. Phys. **39**, 4991 (1968).

[6] Y. Kopelevich et al., Physica C **183**, 345 (1991).

[7] M. E. McHenry et al., Physica C **190**, 403 (1992).